

Hunter Penrose Supplies Ltd
32 Southwark St, London, SE1 1TU
tel: +44207 407 5051
fax: +44 207 378 1800
info@hunterpenrose.co.uk

HUNTER PENROSE

printing materials & equipment

www.hunterpenrose.co.uk

TECHNICAL DATA

Stitching Wire: Round Galvanized

Physical Data

Size	Diameter mm	Metres per kg	Tensile Strength Mpa	Max Elongation %	Zinc Coating g/sq m
20	.90	200	1000-1010	5	13.5 – 16.0
21	.80	253	1000-1010	5	13.5 – 16.0
22	.70	331	1000-1010	5	13.5 – 16.0
23	.60	451	1000-1010	5	13.5 – 16.0
24	.55	536	1000-1010	5	13.5 – 16.0
24.5	.53	577	1000-1010	5	13.5 – 16.0
25	.50	649	1000-1010	5	13.5 – 16.0
26	.46	801	1000-1010	5	13.5 – 16.0

Typical Chemical Composition (core) %

Fe	C	Si	Mn	P	S	Ni	Cr	Cu
99.47	.058	.030	.360	.010	.026	.010	.023	.010